

Amendments to the Claims:

This listing of claims replaces all prior versions and listings of claims in the application:

Listing of Claims:

1. (Currently Amended) An LCD display containing a transmissive optical film comprising a layer containing layered clay particles in a radiation cured binder wherein the total light transmission of the film is greater than 90 percent.
2. (Currently Amended) The LCD display containing a transmissive optical film of claim 1 wherein the radiation cured binder comprises polyfunctional acrylic compounds derived from polyhydric alcohols.
3. (Currently Amended) The LCD display containing a transmissive optical film of claim 2 wherein the radiation cured binder comprises a repeating group selected from the group consisting of ethoxylated trimethylolpropane tri(meth)acrylate, tripropylene glycol di(meth)acrylate, trimethylolpropane tri(meth)acrylate, diethylene glycol di(meth)acrylate, pentaerythritol tetra(meth)acrylate, pentaerythritol tri(meth)acrylate, dipentaerythritol hexa(meth)acrylate, 1,6-hexanediol di(meth)acrylate, and neopentyl glycol di(meth)acrylate.
4. (Currently Amended) The LCD display containing a transmissive optical film of claim 2 wherein the radiation cured binder comprises a repeating group selected from the group consisting of pentaerythritol tetra(meth)acrylate and pentaerythritol tri(meth)acrylate.
5. (Currently Amended) The LCD display containing a transmissive optical film of claim 1 wherein the radiation cured binder comprises acrylate and methacrylate oligomers derived from the group consisting of low-molecular weight polyester resin, polyether resin, acrylic resin, epoxy resin, and polyurethane resin.
6. (Currently Amended) The LCD display containing a transmissive optical film of claim 1 wherein the radiation cured binder comprises a urethane acrylate compound.

7. (Currently Amended) The LCD display containing a transmissive optical film of claim 1 wherein the radiation cured binder comprises an aliphatic urethane acrylate derived from isophorone diisocyanate.
8. (Currently Amended) The LCD display containing a transmissive optical film of claim 1 wherein the radiation cured binder comprises a polyurethane acrylate derived from an aliphatic polyester polyol.
9. (Currently Amended) The LCD display containing a transmissive optical film of claim 1 wherein the particles comprise layered organically modified clay particles.
10. (Currently Amended) The LCD display containing a transmissive optical film of claim 1 wherein the particles have an average size of between 1 and 10 micrometers.
11. (Currently Amended) The LCD display containing a transmissive optical film of claim 1 wherein said particles are present in at least 2% by weight of the layer.
12. (Currently Amended) The LCD display containing a transmissive optical film of claim 1 wherein said particles are present in an amount of less than 50% by weight of the layer.
13. (Currently Amended) The LCD display containing a transmissive optical film of claim 1 wherein the amount of the clay is sufficient to provide a gloss less than 100.
14. (Currently Amended) The LCD display containing a transmissive optical film of claim 1 wherein the amount of the clay is sufficient to provide a gloss less than 80.
15. (Currently Amended) The LCD display containing a transmissive optical film of claim 1 wherein the amount of the clay is sufficient to provide a gloss less than 60.
16. (Currently Amended) The LCD display containing a transmissive optical film of claim 1 wherein the amount of the clay is sufficient to provide a haze less than 30.

17. (Currently Amended) The LCD display containing a transmissive optical film of claim 1 wherein the amount of the clay is sufficient to provide a haze less than 20.

18. (Currently Amended) The LCD display containing a transmissive optical film of claim 1 wherein the amount of the clay is sufficient to provide a haze less than 15.

19. (Currently Amended) The LCD display containing a transmissive optical film of claim 14 wherein the amount of the clay is sufficient to provide a haze less than 20.

20. (Currently Amended) The LCD display containing a transmissive optical film of claim 1 additionally containing a silicone acrylate lubricant.

21. (Currently Amended) The LCD display containing a transmissive optical film of claim 13 wherein the silicone acrylate lubricant is a methacryloxy-functional silicone polyether copolymer.

22. (Currently Amended) The LCD display containing a transmissive optical film of claim 1 wherein said film is deposited upon a transparent polymeric support.

23. (Currently Amended) The LCD display containing a transmissive optical film of claim 22 wherein said support is selected from the group consisting of triacetyl cellulose, polyethylene terephthalate, diacetyl cellulose, acetate butyrate cellulose, acetate propionate cellulose, polyether sulfone, polyacrylic based resins, polyurethane based resin, polyester, polycarbonate, aromatic polyamide, polyolefins, polymers derived from vinyl chloride, polyvinyl alcohol, polysulfone, polyether, polynorbornene, polymethylpentene, polyether ketone, and (meth)acrylonitrile.

24. (Currently Amended) The LCD display containing a transmissive optical film of claim 22 wherein said support is triacetyl cellulose.

25. Canceled.

26. (Currently Amended) The LCD display containing a transmissive optical film of claim 1 comprising a layer containing a radiation cured binder derived from a mixture of (meth)acrylate derivatives of pentaerythritol functionalized aliphatic urethanes.

27. (Currently Amended) The LCD display containing a transmissive optical film of claim 26 wherein the mixture comprises pentaerythritol tetra(meth)acrylate and pentaerythritol tri(meth)acrylate functionalized aliphatic urethanes.

28. (Currently Amended) The LCD display containing a transmissive optical film of claim 1 comprising a layer containing a radiation cured binder derived from isophorone diisocyanate.

29. (Original) A coating dispersion comprising a radiation curable urethane acrylate oligomer, layered clay particles, a radiation sensitive curing agent, and an organic solvent.

30. (Original) The dispersion of claim 29 wherein the clay is organically modified.

31. (Original) The coating dispersion of claim 29 wherein said organic solvent comprises an ester solvent and an aromatic hydrocarbon.

32. (Original) The coating dispersion of claim 29 wherein said the radiation sensitive curing agent comprises a UV sensitive curing initiator.

33. (Currently amended) A method of forming an optical film, comprising: providing a flexible transparent polymeric support, applying to the support a coating of radiation curable binder comprising polyfunctional acrylic compounds[,] and layered clay particles in an organic solvent, and then radiation curing the said coating to form a layer.

34. (Original) The method of claim 33 wherein the coating additionally contains a silicone acrylate.

35. (Previously presented) The method of claim 33 wherein the radiation curable binder comprises a repeating group selected from the group consisting of ethoxylated trimethylolpropane tri(meth)acrylate, tripropylene

glycol di(meth)acrylate, trimethylolpropane tri(meth)acrylate, diethylene glycol di(meth)acrylate, pentaerythritol tetra(meth)acrylate, pentaerythritol tri(meth)acrylate, dipentaerythritol hexa(meth)acrylate, 1,6-hexanediol di(meth)acrylate, and neopentyl glycol di(meth)acrylate.

36. (Previously presented) The method of claim 33 wherein the radiation curable binder comprises a repeating group selected from the group consisting of pentaerythritol tetra(meth)acrylate and pentaerythritol tri(meth)acrylate.

37. (Previously presented) The method of claim 33 wherein the radiation curable binder comprises acrylate and methacrylate oligomers derived from the group consisting of polyester resin, polyether resin, acrylic resin, epoxy resin, polyurethane resin.

38. (Original) The method of claim 33 wherein the radiation curable binder comprises a urethane acrylate containing compound.

39. (Original) The method of claim 33 wherein the radiation curable binder comprises an aliphatic urethane acrylate derived from isophorone diisocyanate.

40. (Original) The method of claim 33 wherein the radiation curable binder comprises a polyurethane acrylate derived from an aliphatic polyester polyol.

41. (Original) The method of claim 33 wherein the particles comprise organically modified clay particles.

42. (Original) The method of claim 33 wherein the particles have an average size of between 2 and 10 micrometers.

43. (Original) The method of claim 33 wherein said particles are present in an amount of at least 2% by dry weight of the layer.

44. (Original) The method of claim 33 wherein said particles are present in an amount of less than 50% by dry weight of the layer.

45.-48 Canceled